



Technical Data: EXECUTIVE ULTRA

Grade: 505

				75
Grammage	g/m ²	ISO 536		75 ± 2.5
Caliper	mm/1000	ISO 534		96 ± 3
Stiffness L&W	MD mN	ISO 2493		min 80
Stiffness L&W	CD mN	ISO 2493		min 35
Roughness Bendtsen	ml/min	ISO 8791-2		140 ± 50
Opacity	%	ISO 2471		min 90.5
Cobb 60	g/m ²	ISO 535		25 ± 5.0
Brightness with UV	D65 %	ISO 2470		113.5 ± 1.5
CIE Whiteness		ISO 11475		169 ± 3.0

Product meets EN 12281, requirements for copy paper for dry toner imaging processes and ISO 9706, requirements for permanence for paper.
 Production processes certified according to ISO 9001, ISO 14001 and OHSAS 18001.

SIGNIFICANCE OF VALUES: 2 SIGMA